


# MetPrep Preparation Procedure – No 250



## Barwell Friable Chondritic Meteorite

	Surface	Abrasive	Pressure		Speed – Dir	Time
			Psi	N		
			Primary Grinding Stage	Paper		

	Surface	Abrasive	Pressure		Speed – Dir	Time
			Psi	N		
			Additional Grinding Stages	Paper		
Paper	P1200g SiC	5		25	150 – Comp	2 mins
	Paper	P2500g SiC	5	25	150 – Comp	1 min
	Planocloth	0.3 µm Alumina	5	25	100 – Comp	8 mins

	Surface	Abrasive	Pressure		Speed – Dir	Time
			Psi	N		
			Polishing Stage	Multicloth		