



## EPO-SET Standard Viscosity Epoxy Resin Mounting Compound



MetPrep's Standard Viscosity Epoxy Cold Mounting compound is a two part system comprising a resin and a hardener.

Ideal when the ultimate edge retention is required. Curing time is typically 4 - 5 hours at room temperature.

11 10 61 EPO-SET Resin 1 Kg  
11 10 66 EPO-SET Hardener 0.25 Kg

### Mixing Instructions

Four Parts Resin - 1 Part Hardener by weight

Mounting moulds of assorted sizes, mixing cups and stirring sticks are also available

MetPrep Technical Data Sheet 0003 - 2015. For further information please contact [sales@metprep.co.uk](mailto:sales@metprep.co.uk)

MetPrep Ltd - Curriers Close, Charter Avenue, Coventry, CV4 8AW - 02476 421222