



## EPO-FLO Ultra-Low Viscosity Epoxy Resin Mounting Compound



MetPrep's New Ultra-Low Viscosity Epoxy Cold Mounting compound is a two part mixture comprising a resin and hardener system

Ideal for use in vacuum impregnation applications such as porous materials and coatings. Curing time is typically 2-2.5 hrs at 40 - 50 C

11 10 65 EPO-FLO Resin 1 Kg  
11 10 66 EPO-FLO Hardener 0.3Kg

### Mixing Instructions

100 Parts Resin - 30 Parts Hardener by weight

Mounting moulds of assorted sizes, mixing cups and stirring sticks are also available

MetPrep Technical Data Sheet 0002 - 2015. For further information please contact [sales@metprep.co.uk](mailto:sales@metprep.co.uk)

MetPrep Ltd - Curriers Close, Charter Avenue, Coventry, CV4 8AW - 02476 421222