



EPO-FLO Ultra-Low Viscosity Epoxy Resin Mounting Compound



MetPrep's New Ultra-Low Viscosity Epoxy Cold Mounting compound is a two part mixture comprising a resin and hardener system

Ideal for use in vacuum impregnation applications such as porous materials and coatings. Curing time is typically 2-2.5 hrs at 40 - 50 C

11 10 65	EPO-FLO Resin	1 Kg	&	11 10 67	EPO-FLO Resin	3 Kg
11 10 66	EPO-FLO Hardener	0.3Kg	&	11 10 68	EPO-FLO Hardener	0.9Kg

Mixing Instructions

100 Parts Resin - 30 Parts Hardener by weight

MetPrep Technical Data Sheet 0002 - 2019. For further information please contact sales@metprep.co.uk

MetPrep Ltd - Falklands Close, Charter Avenue, Coventry, CV4 8AU - 02476 421222